



LOTHERME



LoTherme - 616

Electrode for resisting high abrasion wear with moderate impact at 450°C.

Characteristics :

LoTherme-616 is a high Niobium-Chromium Carbide alloy specially designed to resist high stress grinding abrasion wear with moderate impact, even at elevated temperature of 450°C. The deposit will exhibit surface relief checks.

Applications:

It is suitable for welding of conveyor screws, VRM tyres, Coke chutes, coal mill exhaust fan blades, table liners, screens, oils expeller screws, etc.

WELD METAL HARDNESS : 56 - 62 HRC

Welding Technique :

Remove all the damaged and fatigued metal and clean weld area. Use short arc and stringer bead technique. For High Carbon Steels use preheat up to 300°C. For austenitic manganese steels do not allow the temperature of parts to exceed 150°C and use LoTherme-457 as cushioning layers. Slow cool after welding.

Current Conditions : DC(+) / AC

Size (mm)	5x350	4x350	3.15x350	2.5x350
Dia x Length				
Current Range (Amps)	170-220	130-160	110-140	70-90