



Autotherme Grade-U

Copper Coated Solid Wire for Submerged Arc Welding



CODIFICATION:

AWS: SFA5.23
EA3

CHARACTERISTICS:

Autotherme Grade-U Copper Coated solid wire for submerged arc welding. These are suitable for welding of heat resistant steels.

APPLICATIONS:

Autotherme Grade-U low alloy solid wire is suitable for welding of similar grade steels. The weld metal possesses high tensile strength, and meets the radiographic quality requirements. Especially suitable for welding of tubes matching composition in power plants, Petrochemicals and Suitable for welding of ASTM steels: A516 Gr. B, C & IS 2002 type B, C API Gr. 5L X60-X80 etc.

CHEMICAL COMPOSITION OF SOLID WIRE WT. %:

Element	C	Mn	Si	S	P	Cr	Mo	Cu
Range	0.05-0.17	1.65-2.20	0.20 Max	0.025 Max	0.025 Max	0.15 Max	0.45-0.65	0.35 Max

MECHANICAL PROPERTIES WITH MAXFLUX SAF-723.

Observed	UTS (MPa)	0.2 %YS (MPa)	% EL. (L=4d)	CVN Impact (J) -40 °C
As Welded	620.0	550.0	22.2	>27
PWHT / 620 °C for 1 hr.	590.0	510.0	23.4	50

Packing:	Standard Size	2.5, 3.2 & 4.0 mm
	Quantity	<ul style="list-style-type: none"> ➤ 25 kg. wire in metallic ring. ➤ Identification-Brand name & size is printed on label. ➤ Packed in corrugated cardboard box. ➤ 100Kg, 250kg, 500Kg & 750kg Drum Packing also available on request.

An ISO 9001: 2008 certified company

D&H Sécheron Electrodes Private Limited

44-46, Industrial Estate, Kila Maidan, Indore-452 006, India, Ph: 0731 2412331-2, 4229222 Fax: 0731 4229260
e-mail: tsd@dnhsecheron.net Website: www.dnhsecheron.com

JUN 2017 (Rev.: 03)