

CODIFICATION: AWS/SFA 5.9: ER410

CHARACTERISTICS AND APPLICATIONS:

FW 410 is a solid wire for TIG welding, available in bright finish, gives smooth flow, stable arc and spatter free under optimum welding conditions. It gives radiographic quality weld deposit. Weld metal possesses excellent resistance to corrosion, pitting, abrasion, and impact. It is suitable for joining of similar alloys and for surfacing and overlay applications on unalloyed steels. Ideally suited for surfacing of valves and other components of turbine, steam valves made of 13Cr steel, etc.

TYPICAL CHEMICAL COMPOSITION OF SOLID WIRE:

Element	C	Mn	Si	S	P	Cr
Percent	0.06	0.50	0.40	0.025	0.025	12.0

**TYPICAL MECHANICAL PROPERTIES OF ALL WELD METAL:
(PWHT: 740°C for one Hour)**

UTS (MPa)	Elongation (L=4d) %
550	23.0

SHIELDING GAS : Argon

CURRENT CONDITIONS : DCEN

WELDING POSITION : H, F, VU, OH

PACKING:

STANDARD SIZE	Diameter 1.6 mm, 2.0 mm, 2.5 mm & 3.2 mm in cut lengths of 1000 mm each.
QUANTITY	5 kgs wire put in an air-tight polythene bag and finally packed in a plastic container. Identification – AWS code is punched on both the sides of wire.

An ISO 9001: 2008 certified company

D & H Sécheron Electrodes Pvt. Ltd.

44-46, Industrial Estate, Kila Maidan, Indore-452 006, India, Ph: 0731 2412331-2, 4229222 Fax: 0731 4229260
e-mail: info@dnhsecheron.net Website: www.dnhsecheron.com

November 14, 2015 Rev. 01