



Maxflux HF - 350

Agglomerated hard-surfacing flux for
Submerged Arc Welding



CHARACTERISTICS:

Maxflux HF-350 is a hard surfacing type flux suitable for moderate abrasion resistance applications in combination with EL-8 grade (Autotherme Grade A) wire. Slag removal is easy and weld bead is smooth & shiny. The deposited weld metal is of radiographic quality.

APPLICATIONS:

Maxflux HF-350 is suitable for surfacing of tractor rollers, excavator parts, tracks lines, crane wheels, etc.

ALL-WELD ANALYSIS, WT %:

Autotherme Grade A

C	Mn	Si	Cr	Mo	Cu
0.23	1.0	0.65	3.2	0.20	0.15

ALL-WELD METAL HARDNESS (AS- WELD):

Autotherme Grade A

Hardness on MS plate - 1 st layer	Hardness on MS plate - 2 nd layer	Hardness on MS plate - 3 rd layer
260-290 BHN	340-360 BHN	340-370 BHN

MAJOR CONSTITUENTS:

SiO ₂ + TiO ₂	CaO + MgO	Al ₂ O ₃ + MnO	CAF ₂
25%	5%	50%	25%

BASICITY INDEX : ~0.7

GRAIN SIZE : 0.35 – 1.60 mm

PACKAGING : 25 kgs poly-lined paper bag

RE-DRYING CONDITIONS : 300°-350°C for 2 hours

An ISO 9001: 2008 COMPANY

D&H Sécheron Electrodes Private Limited

44-46, Industrial Estate, Kila Maidan, Indore-452 006, India, Ph: 0731 2412331-2, 4229222 Fax: 0731 4229260
E-mail: tsd@dnhsecheron.net Website: www.dnhsecheron.com

JUN, 2017 (Rev.: 04)